

Australian Chemicals & Coatings Pty Ltd

ABN: 92 884 104 142

69 Quantum Close,
Dandenong South VIC 3175

Ph: +61 (03) 9799 9833

Fax: +61 (03) 9799 9033

sales@auschem.com.au

www.auschem.com.au

WARNING:

**This chemical is formulated
for industrial use only**

Contact with skin or clothing or other improper handling or use of this product may result in bodily harm or other damage. Before using or mixing the contents with other substances, all labels applied to container, the applicable Technical Data Sheet and Material Safety Data Sheet should be read and specific instructions and precautions followed to assure correct use and personal safety.



BRIK-BRITE

INTRODUCTION

BRIK-BRITE is a clear light gel formulated for airless spraying or brushing onto brick and masonry surfaces.

It is formulated to etch the surface and remove pollution build up or "shadows" left behind after paint or graffiti removals.

APPLICATION

BRIK-BRITE is supplied ready for use and can be sprayed using airless spray.

Pressure should be kept low to avoid misting and special care should be taken not to coat any windows as the glass will be etched.

Allow 30 minutes - 2 hours for the product to penetrate and etch the surface, then, high pressure rinse with fresh water.

EQUIPMENT

Equipment should be made from 316 stainless steel.

To give protection to the stainless steel it is advisable to rinse before and after using BRIK-BRITE with 10% Nitric Acid solution.

PVC polyethylene and polypropylene are also suitable to use with BRIK-BRITE.

TYPICAL PROPERTIES

TYPE	Sulphuric, ammonium bi fluoride mixture.
APPEARANCE	Clear slightly yellow gel.
VISCOSITY	2000 - 3000 CPS - 25°C.

SAFETY

Full protection should be worn while using BRIK-BRITE including - coveralls, face shield and PVC gloves.

Any spills on skin should be washed in fresh running water and then treated with calcium gluconate gel. Refer MSDS for full details.

● *Bringing the Best Products to the Surface* ●

Disclaimer: All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the use of or inability to use the product. No suggestion for product use or anything contained herein shall be constructed as a recommendation to use any product in infringement of any patent rights and seller and manufacturer assume no responsibility or liability for any such infringement. We recommend prospective users determine the suitability of this product through independent testing before adopting on a commercial scale.