

Australian Chemicals & Coatings Pty Ltd

ABN: 92 884 104 142

69 Quantum Close,
Dandenong South VIC 3175

Ph: +61 (03) 9799 9833

Fax: +61 (03) 9799 9033

sales@auschem.com.au

www.auschem.com.au

WARNING:

**This chemical is formulated
for industrial use only**

Contact with skin or clothing or other improper handling or use of this product may result in bodily harm or other damage. Before using or mixing the contents with other substances, all labels applied to container, the applicable Technical Data Sheet and Material Safety Data Sheet should be read and specific instructions and precautions followed to assure correct use and personal safety.



AUSEAL HS

BLOOM PREVENTER FOR THE HOT SEAL PROCESS

AUSEAL HS is a liquid for the use in the hot sealing process of anodized aluminium for both natural and electrolytic coloured finishes. It can be used in demineralized water or normal water with SiO₂ content lower than 5 ppm.

ADVANTAGES

- Bloom free sealing
- Non nickel
- Passes all standard seal quality tests i.e. ISO: 2931, 2143, 3210

OPERATING CONDITIONS

Concentration:	2 g/l
Solution temperature:	95°C (Plus)
pH:	6
Immersion time:	3mins/micron

CONSUMPTION

Approximately 10g/M² of aluminium processed – provided recommended working conditions are kept.

EQUIPMENT

Steel tank with facility to raise and maintain the solution temperature at between 96 - 98°C.

SOLUTION PREPARATION

Add AUSEAL HS to achieve a concentration of 2g/L.

● *Bringing the Best Products to the Surface* ●

Disclaimer: All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the use of or inability to use the product. No suggestion for product use or anything contained herein shall be constructed as a recommendation to use any product in infringement of any patent rights and seller and manufacturer assume no responsibility or liability for any such infringement. We recommend prospective users determine the suitability of this product through independent testing before adopting on a commercial scale.

MAINTENANCE AND CONTROL

AUSEAL HS is buffered and is able to stabilize the pH of the solution. If pH corrections are required it is recommended that acetic acid (to decrease) or diluted ammonia (to increase) be used.

pH range 5.5 to 6.0

It is important that material to seal is well rinsed prior to immersion in the AUSEAL HS process. The bath must be dumped when the total salinity exceeds a value of conductivity of 1,800 microsiemens.

EFFLUENT DISPOSAL

Neutralization to the pH range to comply with local authority regulations is sufficient.

HEALTH AND SAFETY

Direct contact with eyes and skin may cause irritation and any splashes should be flushed with copious supply of water.

As with all chemicals care must be exercised during handling and it is recommended that protective clothing, eye protection and rubber gloves be worn.

STORAGE

No special storage procedure is necessary. It is good practice to keep all chemicals in a weatherproof locked area to control access of unauthorized persons and protection from the elements.

PACKAGING

AUSEAL HS is available in 200 kg, non returnable containers and 1000kg returnable containers.