

Specification Sheet



Australian Chemicals & Coatings Pty Ltd

ABN: 92 884 104 142

69 Quantum Close,
Dandenong South VIC 3175

Ph: +61 (03) 9799 9833

Fax: +61 (03) 9799 9033

sales@auschem.com.au

www.auschem.com.au

WARNING:

This chemical is formulated for industrial use only

Contact with skin or clothing or other improper handling or use of this product may result in bodily harm or other damage. Before using or mixing the contents with other substances, all labels applied to container, the applicable Technical Data Sheet and Material Safety Data Sheet should be read and specific instructions and precautions followed to assure correct use and personal safety.

AUSTRIP 6689

INTRODUCTION

AUSTRIP 6689 is a thickened methylene chloride based paint remover, and is designed to remove epoxies, polyurethanes, industrial and household paints from timber, metal or masonry substrates. Contains no phenols, which makes it safer and ideal for household use.

APPLICATION

a) BRUSH APPLICATION - A thick even coat should be spread over surface to be stripped. It should then be left for 5-15 minutes depending on film build up of paint.

When stripping action is complete the paint film can be removed by scraping or high pressure water flushing - repeat process if necessary.

b) AIRLESS SPRAY - Spray an even thick coat on surface. Do not spray on hot surfaces. Shade area if necessary to avoid premature solvent evaporation. High pressure rinse when paint is fully softened and wrinkled - repeat process if necessary.

TYPICAL PROPERTIES

Type	-	Gelled methylene chloride & methanol mixture.
Appearance	-	Red Gel
Specific Gravity	-	1.2
Viscosity	-	Summer formulation – 8-10,000 C.P.S. Winter formulation - 3-6,000 C.P.S.
Coverage	-	Varies according to paint thickness - generally 1/2 - 1 litre to m2.



● *Bringing the Best Products to the Surface* ●

Disclaimer: All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the use of or inability to use the product. No suggestion for product use or anything contained herein shall be constructed as a recommendation to use any product in infringement of any patent rights and seller and manufacturer assume no responsibility or liability for any such infringement. We recommend prospective users determine the suitability of this product through independent testing before adopting on a commercial scale.