

## Australian Chemicals & Coatings Pty Ltd

ABN: 92 884 104 142

69 Quantum Close,  
Dandenong South VIC 3175

Ph: +61 (03) 9799 9833

Fax: +61 (03) 9799 9033

sales@auschem.com.au

[www.auschem.com.au](http://www.auschem.com.au)

### **WARNING:**

**This chemical is formulated  
for industrial use only**

Contact with skin or clothing or other improper handling or use of this product may result in bodily harm or other damage. Before using or mixing the contents with other substances, all labels applied to container, the applicable Technical Data Sheet and Material Safety Data Sheet should be read and specific instructions and precautions followed to assure correct use and personal safety.



## CLASSIQUE STRIP HPR-2

### HOT TANK STRIPPER

#### INTRODUCTION

CLASSIQUE STRIP HPR-2 is a non-methylene chloride based paint stripper that will rapidly penetrate and remove industrial coatings from ferrous and non-ferrous metal surfaces. It is ideal for removal of polyester powdercoat from aluminium extrusions as it "dissolves" the coating instead of lifting it off in sheets.

Epoxy, polyurethane, polyester and acrylic enamel coatings as well as epoxy hybrid and polyester powdercoatings are removed by CLASSIQUE STRIP HPR-2.

#### OPERATIONAL RECOMMENDATIONS

TEMPERATURE	-	65-88°C
CONCENTRATION	-	full strength
TANK CONSTRUCTION	-	mild steel
STRIPPING TIME	-	varies according to film build

After the coating has been penetrated and loosened, rinsing with water will remove any residual paint. On aluminium extrusions the CLASSIQUE STRIPPING SYSTEM is recommended to give a perfectly clean aluminium surface.

To reduce fuming a CLASSIQUE SEAL can be poured on to top of bath.

#### TYPICAL PROPERTIES

TYPE	-	non methylene chloride type mildly
APPEARANCE	-	alkaline solvent. clear to golden yellow
SPECIFIC GRAVITY	-	amine odour. 0.98 approx.

#### SAFETY & HANDLING PRECAUTIONS

Avoid breathing vapour or mist. Avoid contact with eyes and skin.

Wear gloves, goggles and protective clothing when handling. Use with adequate ventilation. Refer to MSDS for further safety information.

● *Bringing the Best Products to the Surface* ●

**Disclaimer:** All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the use of or inability to use the product. No suggestion for product use or anything contained herein shall be constructed as a recommendation to use any product in infringement of any patent rights and seller and manufacturer assume no responsibility or liability for any such infringement. We recommend prospective users determine the suitability of this product through independent testing before adopting on a commercial scale.