

## Australian Chemicals & Coatings Pty Ltd

ABN: 92 884 104 142

69 Quantum Close,  
Dandenong South VIC 3175

Ph: +61 (03) 9799 9833

Fax: +61 (03) 9799 9033

sales@auschem.com.au

[www.auschem.com.au](http://www.auschem.com.au)

### **WARNING:**

**This chemical is formulated  
for industrial use only**

Contact with skin or clothing or other improper handling or use of this product may result in bodily harm or other damage. Before using or mixing the contents with other substances, all labels applied to container, the applicable Technical Data Sheet and Material Safety Data Sheet should be read and specific instructions and precautions followed to assure correct use and personal safety.



# GUARDCOTE

## INTRODUCTION

GUARDCOTE 5122 has been developed to quickly and effectively repair leaks in processing tank liners. Acid and alkali resistant, GUARDCOTE is ideally suited for liquids or fumes. GUARDCOTE repairs joints, cracks, seams, and holes by bonding to the original liner material, and dries within a matter of hours.

GUARDCOTE easily seals leaky pipe flanges on processing tanks, regardless of irregular contours or narrow openings and mating surfaces. Pipes including flanges can be quickly coated inside to eliminate tedious, rigid PVC fabrication.

## APPLICATION

GUARDCOTE can be applied with minimal training and supervision. GUARDCOTE bonds to itself with no loss of adhesion and can be applied in any thickness. Application can be made using a brush, roller or squeeze bottle; no special equipment is needed. Applied unthinned, GUARDCOTE flows into otherwise inaccessible areas and complicated fabrication designs. GUARDCOTE cleans up with MEK (Methyl ethyl Ketone).

Emergency tank repairs can be done with a minimum amount of production downtime. Accelerated cure time makes overnight repairs possible. No special treatment of the substrate material is necessary to achieve an impermeable bond. Compared to contracting expensive tank liner repair, GUARDCOTE is much faster at a fraction of the cost.

## OPERATING CONDITIONS

Adhesion:	Excellent, but may be peeled or scraped off for repair to substrate.
Temperature:	Constant 80°C. - Periodic to 93°C
Cure Time:	total cure – 24 hours. Re-coat – (dip) 20-30 minutes. Brush or roller – 2 hours Note: cure time may be shortened by heat, max. 93°C for 2 hours.

● *Bringing the Best Products to the Surface* ●

**Disclaimer:** All statement, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the use of or inability to use the product. No suggestion for product use or anything contained herein shall be constructed as a recommendation to use any product in infringement of any patent rights and seller and manufacturer assume no responsibility or liability for any such infringement. We recommend prospective users determine the suitability of this product through independent testing before adopting on a commercial scale.

Hardness at cure:	40 Shore A scale.
Shelf Life:	Bulk type, 1 year minimum.
Packaging:	20L and 200L
Type:	Single pack, premixed, ready to apply, liquid polyvinyl Chloride
Colour:	black
Recommendation:	Apply successive coats of different colour to ensure adequate coverage of each coat.

## APPLICATIONS DATA

Brush:	Use fine bristled brush, apply unthinned
Roller:	Use short nap and roller, apply unthinned
Squeeze Bottle:	Apply unthinned to inaccessible corners and joints for Waterproofing and rust proofing.
Spray:	Syphon Feed Operations – thin as much as one to one with MEK. Pressure at gun 15-20 psi: large (90) aircap and fluid tip required.
Airless Operations:	thin approx. 25% (4 parts GUARDCOTE/ 1 part MEK). Spray pressure approx. 2200 psi.
Clean up:	MEK (Methyl Ethyl Ketone)
Safety Equipment:	Industrial respirator with R21 charcoal filters, safety glasses, protective gloves and clothing.